

Envirolok Bag (Tan) Data Sheet

The Envirolok bag is a nonwoven geotextile produced by needle-punching together 100% synthetic staple fibers, in a random network, forming a high strength, dimensionally stable fabric. The synthetic fibers are specially formulated to resist ultraviolet light deterioration, and are inert to commonly encountered soil chemicals. The fabric will not rot or mildew, is non-biodegradable, and is resistant to damage from insects and rodents. The synthetic fiber is stable within a pH range of 2 to 13, making it one of the most stable polymers available for geotextiles today. The Envirolok bag meets the following Minimum Average Roll Values (MARV):

PROPERTIES	TEST METHOD	UNIT	MARV
PHYSICAL			
Weight	ASTM D 5261	oz/yd ²	4.0 (Typ) (135.62 g/m ²)
Dimensions (unfilled)			
Grab Tensile	ASTM D 4632	lbs.	100 (.450 kN)
Grab Elongation	ASTM D 4632	%	50
Puncture Strength	ASTM D 4833	lbs.	65 (.289 kN)
Mullen Burst	ASTM D 3786	psi	210 (1448 kPa)
Trapezoidal Tear	ASTM D 4533	lbs.	45 (.202 kN)
CBR Puncture Resistance	ASTM D 6241	lbs.	310 (1.379 kN)
UV Resistance After 1,000 Hours	ASTM D 4355	% Strength Retained	70
HYDRAULIC			
Permittivity ¹	ASTM D 4491	sec-1	2
Water Flow Rate ¹	ASTM D 4491	gpm/ft ²	140 (5700 l/min/m ²)
Apparent Opening Size ²	ASTM D 4751	U.S. Sieve	70 (.212mm)

1. Handling at the time of manufacturing may change these properties.
2. Apparent Opening Size, (AOS), reported as Maximum Average Roll Value.

To the best of our knowledge, the information contained herein is accurate. However, it is not a warranty or a guarantee and is provided for reference only. We accept no responsibility for results obtained by the application of this information or the safety or suitability of our products either alone or in combination with other products. Final determination of the suitability of any information or material for the use contemplated, of its manner of use, and whether the suggested use infringes on any patents is the sole responsibility of the user.

Revised Date: 01/01/2017